1880

Weekly Report of Gold Deposits Melted at United States Mint.

Date.	Assay No.	Name of Depositor.	Weight before Melting. OZ.	DEC.	Weight after Melting. OZ.	DEC.	Loss. OZ.	DEC.	Loss per ct.	Gain. OZ.	DEC.	Description of Bullion.	Notes of Melter & Refiner.
Jany 19th	156	G. C. Thompson	5	42	5	40		02	40			Bullion	The deposits are from the following sources:
	7	H. Mahn's Sons	1	49	1	49						Coin	
	8		5	30	5	28		02	40			Rings	N. Carolina 2
	9	G. C. Thompson	26	60	24	72	1	88	6 96			Mch Cases & Jewelry	Georgia (1) 4
	60	M. H. Lee	44	72	44	70		02	04			Bars	Alabama (1) 1
	1	D. Lichty & Co.	14	85	14	69		16	1 07			Bar	Wyoming 1
	2	G. C. Thompson	8	09	3	82	4	27	53 37			Jewelry (very base) & Mch Cases	Idaho (1) 1
20th	3	Do	16	31	12	91	3	40	21 35			Mch Cases & Jewelry	Canada — 1
	4	Do	19	34	17	01	2	33	12 26			Do Do	Fine bars (3) 11
	5	A. Loudon Snowden, Supt.	14	87900								Bars, U.S.A.C.N.Y.	Baser Bullion 6
	6	Do	1	51825								Do	Jewelry & cases 7
	7	Do	1	44985								Do	very base 3
	8	Do	2	43090								Do	Coin 7
	9	Do	5	23785								Do	N.Y. Assay Off. 24
	70	Do	5	41390								Do	Total 68
	1	Do	2	95635	51	62380						Do	
	2	Do	4	37555								Do	The losses in melting
	3	Do	4	35320								Do	coin, 0.03%, are fair;
	4	Do	4	41910								Do	in melting finer
	5	Do	4	83075								Do	bullion, 0.07%, are
	6	Do	4	87310								Do	very low, no less than
	7	Do	4	80060								Do	6 deposits being without
	8	McCall & Newman	12	787	12	163	6	24	4 87			King	loss; on melting baser
	9	John Sturtz		545		545						Button	bullion, 3.29%, quite
	80	Chas Noble & Co.	20	42	18	77	1	65	8 25			Amt, N.G.	fair; on melting jew-
	1	I. C. Mecto	26	87	26	87						U.S. Coin	elry & cases, 13¼%,
	2	Geo. Kitchen, Cash.	36	39	36	38		01	03			Bars	a fair average; — on
	3	Dick & Helms	26	86	26	86						U.S. Coin	melting the 3 base
	4	I. C. White	6	57	6	44		10	1 43			Grs & Fillings	deposits, 32.6%,
	5	J. R. Lee	57	88	57	85		03	05			Bar	quite full but not ex-
	6	Simons, Bro. & Co.	17	37	16	09	1	28	7 53			King	cessive. The loss in
	7	H. H. Sheafer & Co.	26	87	26	87						U.S. Coin	melting the amalgam
21st	8	I. B. Lippincott & Co.	6	14	6	14						Bullion, Ala.	of Georgia, 8.97%, and
	9	Emory, Reed & Co.	18	47	18	47						Sor. Coin	that of N. Carolina,
	90	R. D. Langenheim, Secy.	3	79	2	55		24	8 00			Amt, N.G.	8.12%, is rather full
	1	I. A. McCall	20	37	19	93		44	2 20			King	for than usual; — that
	2	A. Loudon Snowden, Supt.	3	93	3	79		14	3 50			Grs & Fgs, Wyoming	of Wyoming, 3½%,
22nd	3	G. C. Thompson	4	64	3	89		75	15 00			Amt, Gen.	is moderate; as is
	4	A. Loudon Snowden, Supt.	5	67300								Bars, U.S.A.C.N.Y.	the loss of 1⅓% on
	5	Do	5	36800								Do	the grains of Canada.
	6	Do	5	87900								Do	Ja C Booth
	7	Do	5	72000								Do	Mint
	8	Do	6	04500								Do	
	9	Do	5	21450	61	73895						Do	
	200	Do	5	30930								Do	
	1	Do	5	52100								Do	
	2	Do	5	64470								Do	
	3	Do	5	77725								Do	
	4	Do	5	88720								Do	
23rd	5	G. C. Thompson	38	82	33	80	5	02	12 87			Jewelry & Mch Cases	
	6	Do	3	16	3	11		05	1 67			Grs, Canada	
	7	Simons, Bro. & Co.	74	03	74	03						Bars	
	8	G. C. Thompson	30	73	26	72	4	01	12 94			Mch Cases & Jewelry	
	9	Do	21	29	19	62	1	67	7 95			Jewelry & Mch Cases	
	10	Do	43	82	43	81		01	02			Sor. Coin	
	1	Do	99	69	99	68		01	01			Do	
	2	Do	12	06	12	04		02	17			Do	
	3	Do	9	69	9	68		01	10			Bar, U.S.A. Oakland	
	4	C. A. Smith & Son	28	77	22	43	6	34	21 86			King & Bars, Base	

Carried forward

18

For week ending

Approximate value, $

Register.

RG104 E-1 Box 120

Report of Gold Deposits
Tailings for week ending
Jan 23rd 1880

RG104 E-1 Box 120

NARA RG104, Entry 1, Box 120

[Abstract:] Report of Gold Deposits melted for week ending January 23, 1880

Weekly Report of Gold Deposits Melted at United States Mint.

[Please see original images for data table.]